


TEXTURE COATING PACKING & CONSUMPTION

			OCALL				4 001		
	Process	Product Code	Dilution	Packing	Number Of Coats	Coating Interval (Hrs)	Consumption	Coverage /Drum	Application Tools
1	Surface Preparation	Surface shall be dry and free form dirt, oil, grease and other contaminants. All cracks or defective substrate shall be repaired with suitable cement filler.							
2	Primer	EMP	Max 5% with clean water	18L	1	3	0.15 - 0.20 ltr/m²	90 - 120 m²	Roller or Brush
3	Texture Coat	MGM	Max 5% with clean water	25 KG	1 - 2	24	4.2 – 5.0 kg/m²	5 - 6 m²	Spray Gun Nozzle (8mm)
		NSC	Max 5% with clean water	25 KG	1 - 2	24	4.2 – 5.0 kg/m²	5 - 6 m²	Spray Gun Nozzle (6.5mm)
		TC	Max 5% with clean water	25 KG	1 - 2	24	3.0 - 3.6 kg/m²	7 - 8 m²	Spray Gun Nozzle (5mm)
4	Top Coat	FSI	FSI Clear	15L	2	-	0.15 - 0.25 ltr/m²	60 - 100 m²	Roller or Brush




















SUZUKA® Stony Coat crafts the authentic effects of natural stones. Its granular surface gives the wall a bold and prominent finish.

CERAMIC COAT

The blend of fine grandeur color sands forms a suave and refined texture, giving the walls an elegant and graceful outlook.

SUZUKA

SUZUKA® MAGIC GRANITE



MGM-302

MGM-317

MGM-307



SUZUKA® CERAMICS



SUZUKA® STONY COAT

The main materials in the following samples are made of natural color sands and ceramics sands, thus the color may differ slightly.

Due to the difference in the base of the surface, the color and pattern may be differ.